

ZERUST® Axxatec™ 87-M VCI RP

ZERUST®/EXCOR® Axxatec™ 87-M is an aqueous-based rust preventative liquid designed for fogging and spraying applications that protect ferrous metals via contact inhibitors and proven ZERUST® Vapor Corrosion Inhibitor (VCI) technology.

ZERUST®/EXCOR® Axxatec™ 87-M is compatible with other metals such as aluminum, copper, brass, and nickel alloys, etc. ZERUST® VCI molecules migrate to provide protection on hard-to-reach void spaces of tanks, packages, enclosures and to be sealed while the product is wet. The rust preventative forms a thin coating that is safe for use on most painted surfaces.

Use Axxatec™ 87-M for corrosion protection during assembly, shipping, and storage. The product comes ready to use and can be applied by fogging or pressurized spray. It is ideal for fogging into complex machine assemblies or packages that contain components with voids and chambers. To gain the benefit of the VCI, use it in a tightly sealed, foggable enclosure or void. The product provides 1 year protection in plain packaging and up to 5 years in hermetically sealed spaces or ZERUST®/EXCOR® VCI packaging.

Application Example

A CKD (Complete Knock Down Kit) is enclosed in multimetal film, and then the interior is fogged with Axxatec™ 87-M and tightly sealed.



Benefits

- Effective water-based RP with VCI
- Ready to use, easy to apply
- Leaves a clear coating
- Foggable VCI protects hard-to-reach surfaces in crevices and voids
- May be used with multiple metal types

Application Type

- Storage
- Mothballing and Long-term storage
- Shipping
- May be used with poly packaging

*Non-Hazardous Disposal: Product in an unopened original container prior to use is non-hazardous waste in the United States according to 40 CFR 261 (no components listed on F, K, P or U lists; not ignitable, not corrosive, not reactive, and not toxic).

Technical Data

Product Information

Ready to use water-based VCI rust preventative liquid.

Application

Apply via spray or fog.
Contact a technical representative for other application methods.

Application temperature	41 to 120°F (5 to 49°C)
Dosage	0.2 fl oz/ft ³ (195 mL/1 m ³)
Removal	Alkaline cleaning agent

Properties

Volatile Content	<15%
Flashpoint	>212°F (100°C)
pH	8 - 9
Viscosity	Water-like
Density (25°C)	0.95-1.05 g/ml

Protection Info

Plain Poly Packaging	1 year
VCI Packaging/hermetically sealed	Up to 5 years
Humidity Chamber ASTM D1735	Exceeds 500 hrs
VCI Test (NACE TM0208-2013)	Pass
Metal types	Ferrous protection only. Multimetal compatible. Do not use on zinc or galvanized steel. Test before use on yellow metals.

Storage

Store in a tightly closed container to preserve VCI. Do not freeze. It may separate when frozen. If frozen, allow to thaw and mix thoroughly. Store in a cool (32 to 85°F / 0 to 30°C), dry place and away from sunlight in original packaging for up to 2 years from the date of shipment.

DECLARATION

This Data sheet and information it contains is considered to be accurate at the date of printing. No representation or warranty, expressed or implied is made as to the accuracy or completeness of the data and information contained in this publication. It is the User's obligation to evaluate and use products safely and within the scope advised in the data sheet and to comply with all applicable laws and regulations.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on validations and tests conducted by Northern Technologies International Corporation/ZERUST® or its partners and are believed to be reliable, but the accuracy or completeness thereof is not guaranteed. We warrant our products will be free from defects when shipped to customer. Our obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Northern Technologies International Corporation/ZERUST® or its partners or agent of the claimed defect within 3 months after shipment of product to customer. Customer shall pay all freight charges for replacement products. We shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products. And any financial claims shall be limited to the value of the products sold. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of the company. The foregoing warranty is exclusive and in lieu of all other warranties, express, implied or statutory, including without limitation any implied warranty of merchantability or of fitness for a particular purpose. In no case shall Northern Technologies International Corporation/ZERUST® be liable for incidental or consequential damages. For full warranty and disclaimer information visit, www.zerust.com/warranty.

©2013-2023 Northern Technologies International Corporation (NTIC). All Rights Reserved. NTIC is the owner of the following trademarks: ActivPak®, Cor Tab®, EXCOR®, Flange Saver®, ICT®, Natur-VCI®, NIT®, Plastabs®, Z-CIS®, Zerion®, ZERUST®, 浩乐特, Z-PAK® and the Color "Yellow". ABRIGO®, UNICO®, and VALENO® are registered trademarks of EXCOR GmbH, a Joint Venture Partner of NTIC.

Availability

ZERUST®/EXCOR® Axxatec™ 87-M is sold as a ready-to-use liquid product. Large quantity pricing is available upon request.

Part Number	Quantity*
350-M-00029PL	5 Gal (19 L)
350-M-00029DR	55 Gal (208 L)

*Product sold in US customary units.
Metric units approximate.

Disposal

Collect waste when removing. Dispose of in accordance with local, national, and international regulations. Avoid release into the environment.

Precautions

- Shake/stir product container before use. Inspect that the product is clear and homogenous before applying.
- Axxatec™ 87-M is a water-based product and will freeze at temperature/environment conditions/substrate surface temperature when water freezes. Do not apply product when there is a chance of water freezing. For low-freezing temperature application, please refer to Axxatec™ 87-MW3 Winterized product.
- Do not reuse product – such as in a circulating spray booth, even when enclosed, as the active VCI component of the product depletes when exposed to air.
- Product has a propensity to foam.
- Do not use for dipping/immersion dip application with an open sump/tank.
- Do not apply the product onto red-hot heated surfaces – such as on surfaces immediately after welding.
- Do not dry surfaces coated with product. Seal enclosure immediately after application.
- Reseal unused, unexposed product in original container immediately after use.
- Do not use on zinc or galvanized steel. Test before use on yellow metals.
- Test before use on painted surfaces.
- Test before use on rubber seals and plastics.
- Remove before painting. Axxatec™ 87-M can be removed with the use of an alkaline cleaning agent.
- Do not place treated metals in direct contact with cardboard packaging or wood.
- Metal may discolor or darken in contact with plastics under very aggressive conditions.

A product of:
Northern Technologies
International Corp
4201 Woodland Road
Circle Pines, MN 55014
USA

Phone. +1 763.225.6600
Fax. +1 763.225.6645
sales@zerust.com
www.zerust.com

